

Technical Data Sheet

FBR
BK COVER BIANCO

Standard Grammages Available

Charateristic	Internal Method	Unit of measurement	Tolerance	180	200	215	250	275	300	350		
Substance Grammatura	POQ-801	g/m2	± 5,0%	180.0	200.0	215.0	250.0	275.0	300.0	350.0		
Thickness Spessore	POQ-803	um	± 5,0%	220.0	252.0	270.0	315.0	355.0	387.0	462.0		
Gloss 20° Lucido 20°	POQ-810	%	min	45.0	45.0	45.0	45.0	45.0	45.0	45.0		
Ganz Whiteness Bianco Ganz	POQ-804	°G	± 10,0	115.0	115.0	115.0	115.0	115.0	115.0	115.0		
Absolute Umidity Umidità Assoluta	POQ-802	%	± 1,0 %	5.0	5.0	5.0	5.0	5.0	5.0	5.0		
Taber Stiffness MD Rigidità Taber L	POQ-846	mN	± 10,0 %	140.0	85.0	100.0	157.0	200.0	260.0	385.0		
Taber Stiffness CD Rigidità Taber T	POQ-846	mN	± 10,0 %	59.0	44.0	50.0	76.0	100.0	130.0	200.0		
Bulk Mano	POQ-805	cm³/g	± 5,0%	1.3	1.3	1.3	1.3	1.3	1.3	1.3		